

Product Specification



Part No.: XB1283605		Color												
Style 1283 Insulated Wire		Per request												
Cross Section 														
Marking BELDEN E357312-S 4AWG AWM STYLE 1283 105C 600V VW-1 - - c AWM I A/B 105C 600V FT1 ROHS														
Description Rated Voltage (V) 600 Rated Temperature (°C) -40~105 Product Standard Certification UL Stranded tinned copper conductor Lead free PVC insulation Uniform insulation thickness to ensure easy stripping and cutting Passes UL VW-1 & CSA FT1 vertical flame test With the character of super flexible With the character of ultraviolet resistant With the character of anti-rat & anti-termite APPLICATION For internal wiring of electronic and electrical equipment Reference Standard UL 62,UL1581及CSA C22.2No.210.2														
Construction Conductor Stranded Tinned Copper AWG 4 Construction (mm) 7/60/0.254 Stranded Dia. (mm) 6.80(Ref.) Insulation Min. Thickness (mm) 1.30 Nom. Thickness (mm) 1.65 Outer Dia. ($\pm 0.40\text{mm}$) 10.10														
Performance Electrical Characteristics Max. Conductor DC Resistance (Ω/km) 0.882 Min. Insulation Resistance at 20°C ($M\Omega \cdot \text{km}$) 12 Dielectric Strength(kV/min) 2														
Mechanical Characteristics: Test Object Insulation Test Material PVC <table> <tr> <td>Before</td> <td>Tensile Strength (Mpa)</td> <td>≥ 10.3</td> </tr> <tr> <td>Aging</td> <td>Elongation (%)</td> <td>≥ 100</td> </tr> </table> Aging Condition 136±2°C x 168 hrs <table> <tr> <td>After</td> <td>Tensile Strength (Mpa)</td> <td>$\geq 70\%$ of original</td> </tr> <tr> <td>Aging</td> <td>Elongation (%)</td> <td>$\geq 65\%$ of original</td> </tr> </table> Flame Test VW-1,FT4 Non-migration (PS&ABS,50°C X24hrsX500g) pass		Before	Tensile Strength (Mpa)	≥ 10.3	Aging	Elongation (%)	≥ 100	After	Tensile Strength (Mpa)	$\geq 70\%$ of original	Aging	Elongation (%)	$\geq 65\%$ of original	
Before	Tensile Strength (Mpa)	≥ 10.3												
Aging	Elongation (%)	≥ 100												
After	Tensile Strength (Mpa)	$\geq 70\%$ of original												
Aging	Elongation (%)	$\geq 65\%$ of original												
Sample Record Sample No. : Original spec no.: Rev.:- Ref. spec No. : SK-B1283-605 Rev.:- 0														
Revision History														
Prepared by: Yanghua 2013/3/1 Approved by: CICICHENG 2013/3/1		Table No.:T100 Rev.: 0 Page 1 of 1												