


- **Economical And Easy** To Install
- Resists Gasoline. **Engine Chemicals And Cleaning Solvents**
- **Expands Up To 150%**
- **Cut And Abrasion** Resistant
- FMVSS 302 Approval



**Hot Knife** 

### Material

**Polyethylene Terepthalate** 

#### Grade

PTN

**Monofilament Diameter** 

.010"

**Drawing Number** 

TF001PET-WD



High thermal and chemical resistance and wide color/size selection make FLEXO® Original PET ideal for customizing and protecting the wires, hoses and cables in custom and classic colors.


## **Put-Ups**

| Nominal<br>Size    | Part<br>#  | Expansion Range |        | Bulk   | Shop  | Available   | Lbs/ |
|--------------------|------------|-----------------|--------|--------|-------|-------------|------|
|                    |            | Min             | Max    | Spool  | Spool | Colors      | 100′ |
| 1/16"              | PTN0.06    | 3/64"           | 3/32"  | 1,000′ | 250′  |             | 0.22 |
| 1/8"               | PTN0.13    | 3/32"           | 1/4"   | 1,000′ | 225′  |             | 0.20 |
| 1/4"               | PTN0.25    | 1/8"            | 7/16"  | 1,000′ | 200′  |             | 0.30 |
| 5/16"              | PTN0.31    | 5/32"           | 15/32" | 500′   | 150′  |             | 0.50 |
| 3/8"               | PTN0.38    | 3/16"           | 1/2"   | 500′   | 125′  |             | 0.57 |
| 7/16"              | PTN0.44    | 7/32"           | 5/8"   | 500′   | 125′  |             | 0.68 |
| 1/2"               | PTN0.50    | 1/4"            | 3/4"   | 500′   | 100′  |             | 0.77 |
| 9/16"              | PTN0.56    | 5/16"           | 7/8"   | 500′   | 100′  | more        | 0.81 |
| 5/8"               | PTN0.63    | 3/8"            | 1"     | 500′   | 100′  | than        | 0.95 |
| 3/4"               | PTN0.75    | 1/2"            | 1 1/4" | 250′   | 75′   | 40          | 1.20 |
| 1"                 | PTN1.00    | 5/8"            | 1 5/8" | 250′   | 65′   |             | 1.34 |
| 1 1/4"             | PTN1.25    | 3/4"            | 1 3/4" | 250′   | 50′   |             | 1.60 |
| 1 1/2"             | PTN1.50    | 1"              | 2 1/8" | 200′   | 40′   |             | 1.96 |
| 1 3/4"             | PTN1.75    | 1 1/4"          | 2 3/4" | 200′   | 30′   |             | 2.45 |
| 2"                 | PTN2.00    | 1 1/2"          | 3 1/2" | 200′   | 50′   |             | 2.60 |
| 2 1/2"             | PTN2.50    | 1 3/4"          | 3 5/8" | 200′   | 50′   |             | 3.80 |
| 3″                 | PTN3.00    | 2 1/2"          | 4 3/4" | 100′   | 50′   | BK,CL,NB,RE | 4.00 |
| 3 END CONSTRUCTION |            |                 |        |        |       |             |      |
| 1/4"               | PT30.25    | 1/8"            | 3/8"   | 1,000′ | 200′  | 4           | 0.39 |
| 9 MIL CON          | ISTRUCTION |                 |        |        |       |             |      |
| 4"                 | PT94.00BK  | 4"              | 6 1/2" | 100′   | 50′   | BK          | 3.80 |
| PET LEAN           |            |                 |        |        |       |             |      |
| 3/4"               | PTLO.75BK  | 1/2"            | 1 1/4" | 250′   | 75′   | BK          | 1.04 |
| 1 1/4"             | PTL1.25BK  | 3/4"            | 1 3/4" | 250′   | 50′   | BK          | 1.19 |

# A Versatile Bundling And Protection Solution

The FLEXO® Original braided from 10 mil polyethylene terepthalate (PET) monofilament yarns. The material has a wide operating temperature range, is resistant to chemical degradation, UV radiation, and abrasion. Used in electronics, automotive, marine and industrial wire harnessing applications where cost efficiency and durability are critical.


The unique braided construction and wide expandability allows quick and easy installation over large connectors and long runs.




















**Abrasion Resistance** Hiah

**Abrasion Test Machine Taber 5150** 

Abrasion Test Wheel Calibrase H-18

**Abrasion Test Load** 500g

**Room Temperature** 77°F

Humidity 72%

Two Broken Filament 300 Test Cycles

Approximately 6 Broken **Filaments 500 Test Cycles** 

Material Destroyed - Very Visible Hole In Matérial 1,150 Test Cycles

**Pre-Test Weight** 4,547.4 mg

**Post-Test Weight** 4,133.9 mg

**Test End Loss Of Mass Point Of Destruction** 413.5 mg



1=No Effect

4=More Affected


RESISTANCE


2=Little Effect

5=Severely Affected

FMVSS-302

3=Affected





# PHYSICAL **PROPERTIES**

| Monofilament Diameter<br>ASTM D-204         | .010       |
|---|------------|
| Flammability Rating<br>FMVSS-302 Approved   | UL94       |
| Recommended Cutting                         | _Hot Knife |
| Colors                                      | >40        |
| Wall Thickness                              | .025       |
| Tensile Strength (Yarn)<br>ASTM D-2256 Lbs  | 7.5        |
| Specific Gravity ASTM D-792                 | 1.38       |
| Moisture Absorption<br>% ASTM D-570         | 12         |
| Hard Vacuum Data<br>ASTM E-595 at 10-5 torr |            |
| TML   | 19         |
| CVCM  |            |
| WVR   | 16         |
| Smoke D-Max<br>ASTM E-662                   | 56         |
| Outgassing                                  | Med        |
| Oxygen Index<br>ASTM D-2863                 | 21         |





