

# **DUNBAR - 3635W**

## 3:1 SHRINK RATIO, DUAL-WALL, FLAME RETARDANT, POLYOLEFIN TUBING

### **Applications**

DUNBAR-3635W is a flexible, high shrink ratio, flame retardant heat shrinkable polyolefin tube with an adhesive lining which flows when heated. It is suitable to seal and protect a wide variety of electrical applications, including wire splices, breakouts, and connectors-to-cable transitions.

#### **Features**

- ★ Shrink ratio: 67% or more in the radial direction, 15% or less in the axial direction
- ★ In stock for immediate shipments
- ★ Continuous operating temperature: 55°C (-67°F) to 110°C (230°F)
- ★ Flammability: UL VW-1 (Jacket only)
- ★ Excellent electrical properties
- ★ High resistance to abrasion, chemicals and oils

#### **Standard**

- ★ AMS-DTL-23053/4 Class 3 (Formerly MIL-DTL-23053/4 Class 3)
- ★ UL 224 (File Number: E319314)
- ★ RoHS Compliant

## **Specification Values**

| Property   |                    |                     | Test Method  | Value                           |  |  |
|------------|--------------------|---------------------|--------------|---------------------------------|--|--|
| Physical   | Llagged            | Tensile strength    | ASTM D 638   | Min. 1300 psi                   |  |  |
|            | Unaged             | Elongation          | A31101 D 030 | Min. 250%                       |  |  |
|            | Fluid              | Tensile strength    | ASTM D 638   | Min. 900 psi                    |  |  |
|            | Resist.            | Dielectric strength | ASTM D2671   | Min. 200 Volts/mil              |  |  |
|            | Heat sho           | ck                  | 250°C/4 hrs  | No cracks, flowing, or dripping |  |  |
|            | Low temp           | perature flex       | ASTM D746    | No crack @-55°C                 |  |  |
|            | Secant M           | 1odulus             | ASTM 882     | Max. 25,000 psi                 |  |  |
| Electrical | Dielectric         | strength            | ASTM D2671   | Min. 300 Volts/mil              |  |  |
|            | Volume resistivity |                     | ASTM D876    | Min. $1x10^{12}\Omega$ - cm     |  |  |
| Chemical   | Copper of          | orrosion            | 121°C/16hrs  | No corrosion                    |  |  |
|            | Fungus resistance  |                     | ASTM G21     | No growth                       |  |  |
|            | Water Ab           | sorption            | ASTM D570    | Max. 1.0%                       |  |  |
|            | Flammab            | oility              | ASTM D2671   | Pass                            |  |  |

Rev. April 2011




Tel: (469) 568-0800 Fax: (469) 568-0808



# **DUNBAR - 3635W**

3:1 SHRINK RATIO, DUAL-WALL, FLAME RETARDANT, POLYOLEFIN TUBING



Fully recovered after heating

#### **Product Dimensions**

Minimum Shrink Temperature: 120°C

|           | Expanded                              |      | Recovered                             |       |   |      |   |      |                    |
|-----------|---------------------------------------|------|---------------------------------------|-------|---|------|---|------|--------------------|
| Size      | Internal<br>Diameter<br>(min.)<br>(D) |      | Internal<br>Diameter<br>(max.)<br>(d) |       | Total Wall<br>Thickness<br>(Nominal)<br>(T) |      | Wall Thickness<br>Adhesive Wall<br>(Nominal)<br>(t) |      | Standard<br>Length |
| Inch Size | ln.                                   | mm   | ln.                                   | mm    | ln.   | mm   | ln.   | mm   | Ft.                |
| 1/8"      | 0.125                                 | 3.2  | 0.038                                 | 0.98  | 0.040                                       | 1.00 | 0.015   | 0.40 | 4                  |
| 3/16"     | 0.188                                 | 4.8  | 0.060                                 | 1.52  | 0.040                                       | 1.00 | 0.019   | 0.50 | 4                  |
| 1/4"      | 0.251                                 | 6.4  | 0.079                                 | 2.00  | 0.040                                       | 1.00 | 0.023   | 0.59 | 4                  |
| 3/8"      | 0.374                                 | 9.5  | 0.118                                 | 3.00  | 0.047                                       | 1.20 | 0.025   | 0.65 | 4                  |
| 1/2"      | 0.503                                 | 12.8 | 0.156                                 | 3.98  | 0.056                                       | 1.43 | 0.031   | 0.79 | 4                  |
| 3/4"      | 0.767                                 | 19.5 | 0.236                                 | 6.00  | 0.078                                       | 2.00 | 0.042   | 1.09 | 4                  |
| 1"        | 1.000                                 | 25.4 | 0.314                                 | 8.00  | 0.079                                       | 2.03 | 0.037   | 0.93 | 4                  |
| 1-1/2"    | 1.570                                 | 40.0 | 0.510                                 | 12.95 | 0.090                                       | 2.30 | 0.047   | 1.20 | 4                  |

<sup>\*</sup>Metric sizes available for special orders.

Rev. April 2011



P.O Box 112218, Carrollton, Texas 75011-2218

Tel: (469) 568-0800 Fax: (469) 568-0808