952 FLEX-GUARD PE/HD SERIES Heavy Duty Expandable Monofilament Sleeving

DESCRIPTION

- Braided sleeving produced from .015 mil polyester PET (Polyethylene Terephthalate) monofilament
- Heavy duty protective sleeving
- UL recognized for use up to 125°C
- CSA approved and rated for use up to 125°C
- Standard color: Black or Clear

FEATURES

- Demonstrates excellent chemical and fungus resistance
- Provides good mechanical properties with additional coverage
- Resistance to abrasion and cut-through make it ideal for many industrial and electrical applications
- Excellent chemical resistance permits use in harsh fluid environments
- Open weave construction allows expansion above or below original diameter
- Easy to apply and slip on quickly over irregular shapes
- Good flexibility retained at low temperatures, allows for easy flexing in any direction
- Can neatly capture a number of different sized items within one length

APPLICATIONS

- Most commonly used over wires, wire bundles and harnesses, cable assemblies, flat ribbon cable, tubing and hoses to provide a tough, durable protection
- Open weave construction allows for complete drainage, prevents condensation and provides for dissipation of heat and moisture
- Ideal for application in machine tools, automatic equipment and robotics where wires and tubes are required to flex freely during operating cycles
- Suitable for exposure to all weather conditions

62	PART NUMBERS (COLOR: BLACK)	SIZE NOMINAL ID	SIZE RANGE	APPROX. WEIGHT/1000 FT.	STD. SPOOL PUT-UP
3	95220375	3/8"	3/16" - 3/4"	8.3 lbs.	500 ft.
9	95220625	5/8"	5/16" - 1"	11.4 lbs.	250 ft.
62	95221000	1"	1/2" - 1-1/2"	17.4 lbs.	250 ft.
	95221500	1-1/2"	1" - 2"	28.2 lbs.	250 ft.
۲	95222000	2"	1-1/2" - 3"	34.8 lbs.	100 ft.
	95223000	3"	2-1/2" - 4-1/2"	43.5 lbs.	100 ft.
5	95224000	4"	3" - 5-1/4"	44.0 lbs.	100 ft.

The information provided above represents average values and is believed to be reliable. Alta Technologies, Inc. makes no warranties as to its accuracy and disclaims any liability in connection with its use. It is provided for general use only and should not be incorporated into any specific specifications.

FLUID RESISTANCE

Testing verifies that there is virtually no effect on the tensile strength and only a slight reduction in elongation (approx. 5%) of FLEX-GUARD PE/HD when exposed to the following fluids: Cleaning Fluid, De-Icing Fluid, Fuel Oil, Gasoline, Hydraulic Fluid, Lubricating Oil, Salt Water and Solvents







PROPERTIES	TEST METHOD	PERFORMANCE	
Tensile Strength	ASTM D-876	90,000 psi	
Elongation	ASTM D-876	25% 1.31	
Specific Gravity	ASTM D-876		
Moisture Absorption (24 hours)	ASTM D-570	0.08%	
Shrinkage @ 180°C		4%	
Max. Operating Temperature	UL 224	125°C	
Melt Temperature	ASTM D-2117	250°C	
Low Temperature Flexibility	MIL I 23053-E	-70°C	
Flexural Modulus 103 psi @ 73°F	ASTM D-790	400	
Fungus Resistance	MIL STD 810 (508)	No Growth	
Copper Corrosivity	MIL I 23053	No Effect	

