

EXRAD FXD Door / Hatch Cable

-70 - 150°C

EXRAD FXD is a high performance wire designed specifically for flexibility and long flex life. Do not be fooled by wires that bend easily at ambient temperatures. The temperature performance range of FXD is -70° C to 150° C. FXD exceeds SAE J1128 TXL requirements. Standard connectors match exactly and seal well with FXD because it is the same size as other common automotive conductors. Even though it is flexible, FXD has enough column strength to allow easy insertion through the seals of water-resistant connectors. The high temperature performance and fluid resistance of FXD means it can be routed throughout the vehicle including the engine compartment. Superior abrasion and pinch resistance ensures durability and helps keep the wire harness safe and free from defect even with hundreds of thousands of flexes.

Given today's longer warranties you need a wire that will perform more bends and twists than ever before. EXRAD FXD will perform up to 9 times more flexing than conventional wire. FXD processes very well on automated high speed cut and strip equipment. The end result is an automotive wire ideally suited to applications where a combination of flexibility, long flex life and performance is required.

Benefits and Features

Much Longer Flex Life
Ultra Flexible
Standard Dimensions of SAE J1128 TXL
Fluid Resistant
-70°C to 150°C Temperature Range
Superior Processing

Applications

Including but not limited to:

Conventional Doors Sliding Doors

Hatches Hood

Joy Stick Controls

Part Number	Standard Conductors		. Dia of ductor		ılation kness	Nom. OD		Finished Weight	Ampacity
	Bare Copper	in.	mm.	in.	mm.	in.	mm.	(lbs/mft)	
EXRAD-FX22-XX	22 (37/37)	.031	.79	.016	.41	.063	1.60	3.56	11
EXRAD-FX20-XX	20 (41/36)	.035	.89	.016	.41	.070	1.78	4.73	15
EXRAD-FX18-XX	18 (41/34)	.047	1.19	.016	.41	.078	1.98	6.67	21
EXRAD-FX16-XX	16 (41/32)	.057	1.83	.016	.41	.089	2.26	9.99	28
EXRAD-FX14-XX	14 (105/34)	.071	1.85	.016	.41	.103	2.62	15.08	46
EXRAD-FX12-XX	12 (105/32)	.095	2.41	.018	.46	.128	3.25	23.96	60
EXRAD-FX10-XX	10 (105/30)	.112	2.84	.018	.46	.156	3.96	38.40	80

^{*}Ampacity 150°C rated single-insulated conductor in free air at 40°C ambient air temperature.







EXRAD FXD								
]	SAE J- 1128 TXL Req.	EXRAD 20 FXD Typical Performance						
Flex Life								
Flex Test	Per Modified ISO 14572		NA	160,000				
Dielectric Strength								
Dielectric Test	Wet Dielectric after 5 hour soak		1 kV 1 min.	5 kV 30 min.				
Flame Resistance								
Flame Test	Maximum time after burn		70 Sec	4 sec				
Thermal Performance								
Cold Bend	4 hours at temperature no cracks / breakdown	-40°C	-70°C					
Temperature Rating	240 Hours @180°C heat aging	155°C	180^{0} C					
Temperature Rating	3000 Hours @150 ⁰ C		125°C	150°C				
Mechanical Properties								
Tensile	Minimum psi	1500	3300					
Elongation	Minimum %		150	430				
Abrasion	Sand Paper Resistance Length in. (14 awg)		18	45				
Abrasion	Scrape Cycles (14 awg)		None	148				
Pinch	Pounds		9	18				
Ozone Resistance								
Ozone Test	192 Hours @ 65 ⁰ C 100 pphm no cracks		Pass	Pass				
Fluids								
Engine Oil	ASTM D471, IRM-902	$50 + /-3 {}^{0}\text{C}$	15% Max.	1.6%				
Gasoline	ASTM D471 Ref. Fuel C	23 +/-5 °C	15% Max.	<1%				
Brake Fluid	SAE-J-1703	$50 + /-5 {}^{0}\mathrm{C}$	None	<1%				
Ethanol	85% Ethanol +15% ASTM D471, Ref. Fuel C	23 +/-5 °C	15% Max.	<1%				
Diesel Fuel	ASTM D471, 90% IRM-903 + 10% p-xylene	23 +/-5 °C	15% Max.	1.8%				
Power Steering	ASTM D471, IRM-903	50 +/-3 °C	30% Max.	1.2%				
Auto Transmission	Citgo #33123 SAE-J311	$50 + /-3 {}^{0}\text{C}$	25% Max.	5.3%				
Methanol			25% Max.	<1%				
Engine Coolant	50% Ethylene Glyco + 50% distilled Water	$50 + /-3$ 0 C	15% Max.	0%				
Battery Acid	H_2SO_4 Specific Gravity = 1.260 +/005	23 +/-5 °C	5% Max.	<1%				

We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss and damage arising from the handling and use of our products whether used alone or in combination with other products



