

# **FEP1.67**

### 1.67:1 SHRINK RATIO, FLUORINATED ETHYLENE PROPYLENE TUBING

## **Applications**

FEP1.6 is a flame retardant heat shrinkable fluorinated ethylene propylene tube. It has a high shrink ratio with a medium wall.

#### **Features**

- ★ In stock for immediate shipments
- ★ Shrink ratio: 1.67:1 shrink ratio in the radial direction, ± 15% in the axial direction
- ★ Continuous operating temperature: 75°C to 200°C
- ★ High resistance to chemicals and oils

#### **Standard**

- ★ MIL-DTL-23053/11 Class 2
- ★ RoHS Compliant

## **Specification Values**

Property		Test Method	Value	
	Specific Gravity	ASTM D792	2.13-2.17 grams/cm <sup>3</sup>	
Physical	Elongation	ASTM D638	250-330%	
	Tensile Strength	ASTM D638	2800-5000 psi	
	Flexural Strength	ASTM D790	No break	
	Compressive Strength	ASTM D695	2000 psi	
	Flexural Modulus	ASTM D790	78000-92000 psi	
	Hardness Durometer	ASTM D636	D-55	
	Abrasion Resistance	Taber	14-20 (1000 revs)	
Electrical	Dielectric Strength	ASTM D149	500 (125 MIL)	
	Dielectric Strength	ASTM D149	≥1400 (10 MIL)	
	Volume Resistivity	ASTM D257	$>10^{18}\Omega$ - cm	
	Surface Resistivity	ASTM D257	$>10^{17}\Omega$ - cm	
General	Chemical/Solvent Resistance	ASTM D543	No corrosion	
	Water Absorption	ASTM D570	<0.01	
	Deformation Under Load	ASTM D621	No growth	
	Flammability Rating	UL 94	V -0	

Rev. Feb 2015




Fax: (469) 568-0808



# **FEP1.67**

### 1.6:1 SHRINK RATIO, FLUORINATED ETHYLENE PROPYLENE TUBING



Fully recovered after heating

Product Dimensions Minimum Shrink Temperature: 210 °C (over 1" Dia. 221 °C)

Product Dimensions   Minimum Shrink Temperature: 210 °C (over 1" Dia. 221 °C)									
	Expanded		Recovered						
Size	Internal Diameter (min.) (D)		Internal Diameter (max.) (d)		Total Wall Thickness (t)		23053/11		
	ln.	mm	ln.	mm	ln.	mm	Class 2		
3/32"	.093	2.36	.056	1.42	.008 ± .003	.203 ± .076	201		
1/8"	.125	3.18	.075	1.91	.010 ± .003	.254 ± .076	202		
3/16"	.188	4.78	.115	2.92	.010 ± .003	.254 ± .076	203		
1/4"	.250	6.35	.150	3.81	.010 ± .003	.254 ± .076	204		
3/8"	.375	9.53	.225	5.72	.012 ± .003	.305 ± .076	205		
1/2"	.500	12.70	.300	7.62	.015 ± .004	.381 ± .102	206		
3/4"	.750	19.05	.450	11.43	.020 ± .004	.508 ± .102	207		
1"	1.000	25.40	.600	15.24	.025 ± .005	.635 ± .127	208		
1-1/2"	1.500	38.10	.900	22.86	.030 ± .005	.762 ± .127	209		
2"	2.000	50.80	1.200	30.46	.030 ± .005	.762 ± .127	210		

Rev. Feb 2015



Fax: (469) 568-0808