



150
UL 3265
125°C - 150V
CSA AWM

Irradiation Cross-Linked Polymeric Insulation

UL 3265 125°C 150V CSA AWM
ROHS and CE Compliant

Champlain Cable **Exar® 150** is the premium heat-defying cable in its class. Its irradiation cross-linked polymeric insulation possesses remarkable mechanical, flame resistance and electrical properties. Exar 150 processes extremely well on the latest high speed cut and strip machines. Processing costs are reduced by avoiding problems such as solder iron shrink-back, insulation creeping and poor abrasion resistance. This product has unusually high chemical resistance including many potting compounds, toners and solvents. Save money by avoiding costly scrap and rework.



*Ampacity 150°C rated single-insulated conductor in free air at 40°C ambient air temperature

Product Number	Standard Conductors Tin Copper	Nom. Dia of Conductor		Insulation Thickness		Nom. OD		Finished Weight (lbs/mft)	Ampacity
		in.	mm.	in.	mm.	in.	mm.		
3265-28/XX-B0	28 (7/36)	.015	.38	.010	.25	.036	0.91	1.10	1
3265-26/XX-A0	26 (1/26)	.015	.38	.010	.25	.038	0.97	1.32	3
3265-26/XX-B0	26 (7/34)	.019	.48	.010	.25	.040	1.02	1.49	3
3265-26/XX-E0	26 (19/38)	.020	.51	.010	.25	.040	1.02	1.55	3
3265-24/XX-A0	24 (1/24)	.020	.51	.010	.25	.042	1.07	1.86	7
3265-24/XX-B0	24 (7/32)	.024	.61	.010	.25	.045	1.14	2.09	7
3265-24/XX-E0	24 (19/36)	.024	.61	.010	.25	.045	1.14	2.14	7
3265-22/XX-A0	22 (1/22)	.025	.64	.010	.25	.047	1.19	2.68	14
3265-22/XX-B0	22 (7/30)	.030	.76	.010	.25	.051	1.26	3.00	14
3265-22/XX-E0	22 (19/34)	.031	.79	.010	.25	.052	1.32	3.12	14
3265-20/XX-A0	20 (1/20)	.032	.81	.010	.25	.054	1.37	3.97	18
3265-20/XX-B0	20 (7/28)	.038	.97	.010	.25	.059	1.50	4.45	18
3265-20/XX-E0	20 (19/32)	.038	.97	.010	.25	.060	1.52	4.67	18
3265-18/XX-A0	18 (1/18)	.040	1.02	.010	.25	.062	1.58	5.93	25
3265-18/XX-B0	18 (7/.0152)	.045	1.14	.010	.25	.066	1.67	6.13	25
3265-18/XX-D0	18 (16/30)	.045	1.14	.010	.25	.066	1.67	6.05	25
3265-16/XX-F0	16 (26/30)	.058	1.47	.010	.25	.078	1.98	9.42	31



Manufacturing Locations:
Colchester, Vermont
El Paso, Texas
Leeds, Massachusetts



Irradiation Cross-Linked Polymeric Insulation

150

UL 3265

125°C - 150V

CSA AWM

PROPERTIES	EXAR® 150	
Approvals / Listings:		
UL	STYLE 3265	
CSA	AWM 150°C 300V	
Physical: *		
Temperature Rating	125 150°C	
Voltage Rating (Vrms)	300V	
Flexibility - 7 days @ 180 °C	Passes	
Cold Bend - 4h @ -65°C	Passes	
Deformation	18%	
Shore "A" Hardness	95	
Shore "D" Hardness	42	
Bend Radius	3 X overall diameter	
Tensile Strength: *		
Unaged	2000 PSI	
Retention after 7 days @ 180 °C	Passes (100%)	
Elongation: *		
Unaged	250%	
Retention after 7 days @ 180 °C	95%	
Flame Test: *		
UL VW-1	Passes	
IEEE Std. 383-1974	Passes	
Chemical Resistance:		
Acetone	swell @23°C/24h	5-10%
Acid – H2SO4 S.G. 1.260 5%	swell @23°C**	<1%
Engine Oil – ASTM D-471 IRM-902	swell @50°C**	1.80%
Benzene	swell @23°C/24h	Not recommended
Epoxy	swell @23°C/24h	<5%
Gasoline – ASTM D-471 Fuel C	swell @23°C**	<1%
Methanol	swell @23°C**	<1%
Toluene	swell @23°C**	Not recommended
Xylene	swell @23°C**	Not recommended
Electrical: *		
Dielectric Constant		3.1
Dielectric breakdown strength (Vrms)		12,000
Oxygen Index:		24
Gamma Radiation Resistance – Total:		
Integral dose (Cobalt 60 @ a rate of less than 1 megarad/hr.)		200 megarads

* Properties are tested to UL 758 and UL 1581.

** Percent swell SAE J-1128 TXL

We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss and damage arising from the handling and use of our products whether used alone or in combination with other products

Sales Offices:

