



DUNBAR – 1625W

2:1 SHRINK RATIO, DUAL-WALL, FLEXIBLE, POLYOLEFIN TUBING

Applications

DUNBAR-1625W is designed for general purpose applications such as the insulation and strain relief of electrical connections and terminations, light-duty harnessing, jacketing and bundling. The adhesive lining forms an environmental seal that helps protect against moisture.

Features

- ★ Shrink ratio: 50% or more in the radial direction, 5% or less in the axial direction
- ★ In stock for immediate shipments
- ★ Continuous operating temperature: - 55°C (-67°F) to 110°C (230°F)
- ★ Flammability: UL VW-1 (Jacket only except clear)
- ★ Excellent electrical properties

Standard

- ★ AMS-DTL-23053/4 Class 2 (Formerly MIL-DTL-23053/4 Class 2)
- ★ UL 224 (File Number: E319314)
- ★ RoHS Compliant

Specification Values

Property		Test Method	Value	
Physical	Unaged	Tensile strength	Min. 1500 psi	
		Elongation	Min. 200%	
	Fluid Resist.	Tensile strength	Min. 1000 psi	
		Dielectric strength	Min. 400 Volts/mil	
	Heat shock		250°C/4 hrs	No cracks, flowing, or dripping
	Low temperature flex		ASTM D746	No crack @-55°C
	Secant Modulus		ASTM D882	Max. 25,000 psi
Heat Resistance		ASTM D2671	No cracks	
Electrical	Dielectric strength		ASTM D2671	Min. 500 Volts/mil
	Volume resistivity		ASTM D876	Min. $1 \times 10^{12} \Omega$ - cm
Chemical	Copper corrosion		121°C/16hrs	No corrosion
	Fungus resistance		ASTM G21	No growth
	Water Absorption		ASTM D570	Max. 0.5%
	Flammability		ASTM D2671	Pass

Rev. May 2011




Dunbar Products, LLC
Your Stocking Partner for Quality Components

P.O Box 112218, Carrollton, Texas 75011-2218
Tel: (469) 568-0800
Fax: (469) 568-0808



DUNBAR – 1625W

2:1 SHRINK RATIO, DUAL-WALL, FLEXIBLE, POLYOLEFIN TUBING



Product Dimensions

Minimum Shrink Temperature: 120°C

Size	Expanded		Recovered					
	Internal Diameter Minimum (D)		Internal Diameter Maximum (d)		Minimum Total Wall Thickness (Total Wall) (T)		Nominal Wall Thickness (Adhesive Wall) (t)	
	In.	mm	In.	mm	In.	mm	In.	mm
1/8"	0.125	3.2	0.062	1.57	0.017	0.43	0.008	0.20
3/16"	0.187	4.7	0.093	2.36	0.017	0.43	0.008	0.20
1/4"	0.250	6.4	0.125	3.18	0.022	0.56	0.008	0.20
3/8"	0.375	9.5	0.187	4.75	0.022	0.56	0.012	0.30
1/2"	0.500	12.7	0.250	6.35	0.022	0.56	0.012	0.30
3/4"	0.750	19.1	0.375	9.53	0.027	0.69	0.012	0.30
1"	1.000	25.4	0.500	12.7	0.030	0.76	0.012	0.30
1-1/2"	1.500	38.1	0.750	19.1	0.034	0.86	0.012	0.30

Rev.May 2011



Dunbar Products, LLC
Your Stocking Partner for Quality Components

P.O Box 112218, Carrollton, Texas 75011-2218
Tel: (469) 568-0800
Fax: (469) 568-0808