DERAY® KYF 190

INSULATE SEAL PROTECT



THIN WALL MODIFIED CROSS-LINKED FLUOROPOLYMER

Flexible, high temperature PVDF thin wall heat shrink tubing with extreme chemical resistance ideal for protection of components in a wide range of severe temperature and chemical environments

FEATURES AND BENEFITS

- 2:1 shrink ratio
- Flexible
- Highly flame retardant
- High temperature resistance
- Excellent chemical and solvent resistance
- Continuous operating temperature: -55°C to 190°C
- Shrink temperature: 175°C

STANDARDS

- UL 224 VW-1
- CSA C22.2 No. 198.1
- SAE-AMS-DTL-23053/18 Class 2

TYPICAL APPLICATIONS

 Protective see through covering for high temperature and aggressive chemical applications




THIN WALL MODIFIED CROSS-LINKED FLUOROPOLYMER

DERAY® KYF 190

DIMENSIONS

	EXPANDED INTERNAL DIAMETER (MIN) D		RECOVERED					
Order Number			Internal Diameter (max) d		WALL THICKNESS (NOM) W		LENGTHS	
	ММ	IN	ММ	IN	ММ	IN	М	FT
0047	1.2	3/64	0.6	0.023	0.24	0.009	300	984
063	1.6	1/16	0.8	1/32	0.24	0.009	300	984
0094	2.4	3/32	1.2	3/64	0.24	0.009	300	984
0125	3.2	1/8	1.6	1/16	0.24	0.009	300	984
0187	4.8	3/16	2.4	3/32	0.24	0.009	300	984
0250	6.4	1/4	3.2	1/8	0.30	0.012	300	984
0375	9.5	3/8	4.8	3/16	0.30	0.012	150	492
0500	12.7	1/2	6.4	1/4	0.30	0.012	100	328



ORDERING

- Select a dimension which will shrink snugly over the component to be covered. If recovery is restricted the resultant wall thickness will be less than specified.
- Select options:
 - Color: Black (BK), Clear (natural)
 - Printing: Printed or Unprinted
- Please specify the product name, order number and options you require
- Order Example: DERAY® KYF 190, 0047, black, unprinted, 984 ft lengths

Please contact your Customer Service Representative for information on custom colors, sizes, lengths and material data sheet.

liability regarding its use. Our responsibilities are only those listed in our Standard Terms and Conditions of Sale for these products. In no instance will we be liable for any eventual, indirect or consequential damage or damages arising from the sale, resale, transfer, use or misuse of the product.