

## **NEMA WC 27500**

### **Shielded and Unshielded Military**

### **APPLICATION**

The NEMA WC 27500 specification is commonly used to describe both shielded and unshielded cable constructions for avionics, aerospace, and airframe applications. The specification allows the user a wide variety of construction choices. Circuit identification, conductor size, insulation type, number of conductors, shielding material, and jacket compound may all be specified using this document.

Although there is not a QPL required for WC 27500 in itself, the basic component wires are QPL. Thus, the producer of the finished cable must be a qualified source under the applicable basic wire specification, or must provide evidence that Qualified wire was used in the construction of the cable.

**TABLE 1-Basic Wire Specifications** 

Since RSCC Aerospace & Defense has a large variety of military QPL approvals, it is able to provide one of the widest ranges of WC 27500 contructions of any source in the wire and cable industry. Although this brief catalog sheet cannot list all the detailed testing and specification requirements contained in the complete WC 27500 document, we have summarized the major construction features of the specification and listed those that RSCC Aerospace & Defense produces. Please refer to WC 27500 for complete performance and test details.



#### **ANATOMY OF A PART NUMBER**



All the basic wire specifications listed below may be supplied by RSCC Aerospace & Defence as components in WC 27500 cables. These range from low temperature PVC/Nylon leads through high performance, high temperature constructions. The basic wire specification, part number designation symbol, and a brief description of the insulation type are listed in Table 1.

	Symbol	Basic Wire Specifications	Insulation Type	Temp. Rating	Voltage
	Α	SAE AS50861/1	PVC/NYLON	150°C	
	В	SAE AS50861/2	PVC/NYLON/BRAIDS	150°C	
	SB	SAE AS22759/32	XLETFE	150°C	
	SC	SAE AS22759/33	XLETFE	200°C	
	SD	SAE AS22759/34	XLETFE	150°C	
	SE	SAE AS22759/35	XLETFE	200°C	
	SM	SAE AS22759/41	XLETFE	200°C	
	SN	SAE AS22759/42	XLETFE	200°C	
. С	SP	SAE AS22759/43	XLETFE	200°C	
	SR	SAE AS22759/44	XLETFE	200°C	600V
	SS	SAE AS22759/45	XLETFE	200°C	
	ST	SAE AS22759/46	XLETFE	200°C	
	TE	SAE AS22759/16	ETFE	150°C	
	TG	SAE AS22759/18	ETFE	150°C	
	MH	SAE AS81044/9	XL POLY/KYNAR	150°C	
	MJ	SAE AS81044/10	XL POLY/KYNAR	150°C	
	MK	SAE AS81044/11	XL POLY/KYNAR	150°C	
	ML	SAE AS81044/12	XL POLY/KYNAR	150°C	
	MM	SAE AS81044/13	XL POLY/KYNAR	150°C	

The specification also allows a wide variety of jacket materials in both single and double wall constructions. The double jacketed constructions are to be used in conjunction with the double shields listed above. A double jacket is applied using two shields with the inner jacket isolating the shields, plus an outer jacket.

Su	Single Shield	Double Shield	Shield Material	Temp. Rating
escriptions	U	-	Not Shielded	-
	T	V	Tin plated copper, round	150°C
Des	S	W	Silver plated copper, round	200°C
	N	Y	Nickel plated copper, round	260°C
Shield	F	Z	Stainless steel, round	400°C
2-3	С	R	Nickel clad copper, round	400°C
ш	М	K	Silver plated high strength, copper alloy, round	200°C
TABL	Р	L	Nickel plated high strength, copper alloy, round	260°C

	Single Jacket	Double Jacket	Jacket Material	Temp. Rating
	00	00	No Jacket	-
ı	01	51	Extruded white PVC	90°C
lypes	02	52	Extruded clear nylon	105℃
٩	05	55	Extruded clear FEP	200℃
_	08	58	Extruded white irradiated PVDF	150℃
Jacket	09	59	Extruded white FEP	200℃
פַ ו	10	60	Extruded clear PVDF	125℃
٦.	14	64	Extruded white ETFE	150℃
'n	15	65	Extruded clear ETFE	150℃
ا بد	20	70	Extruded white PFA	260℃
20 70 Extrude 21 71 Extrude 23 73 Extrude		71	Extruded clear PFA	260℃
A	23	73	Extruded white irradiated ETFE	200℃



# **NEMA WC 27500**

### **Recommended Shield and Jacket Types** for Components Listed

### **CONDUCTOR**

Various platings and strandings

### **INSULATION**


Various insulation types

#### **SHIELD**

Various materials (available unshielded)

### **JACKET**

Various materials (available unshielded)



Symbol	Basic Wire Spec- ifications	Shield Material	Jacket Material	Temperature Rating	Voltage Rating
Table 1	Table 1	Table 2	Table 3		
A B	SAE AS50861/1 SAE AS50861/2	U T V	00 01 51	105°C 90°C 90°C	600V 600V
MH MJ MK ML MM	SAE AS81044/9 SAE AS81044/10 SAE AS81044/11 SAE AS81044/12 SAE AS81044/13	U T V	00 08 58	150°C 150°C 150°C	600V 600V 600V
SB SD	SAE AS22759/32 SAE AS22759/34	U T V	00 23 73	150°C 150°C 150°C	600V 600V 600V
SC SE SP SR	SAE AS22759/33 SAE AS22759/35 SAE AS22759/43 SAE AS22759/44	U S W	00 23 73	200°C 200°C 200°C	600V 600V 600V
SM SN SS ST	SAE AS22759/41 SAE AS22759/42 SAE AS22759/45 SAE AS22759/46	U N Y	00 23 73	200°C 200°C 200°C	600V 600V 600V

The above part numbers represent the more popular constructions. However, other designs are available upon request.All products are manufactured to meet RoHS compliance, except when material requirements prohibit it. For RoHS exceptions, please contact our sales department.

