FLEXO® F6 FR

■ V \	W -1	I, F/	4R	25
--------------	-------------	-------	----	----

- Easy, Cost And Labor **Effective Wraparound** Installation
- More Flexible Than Spiral **Wrap Of Split Convoluted Tubing**
- 25% Edge Overlap
- Resists Chemicals & Solvents
- Cut And Abrasion Resistant



Material

PET

Grade

F6F

Monofilament Diameter

.008" - .015"

Drawing Number

TF001F6F-WD

	Comment of the							
Nominal Size	Part #	Wall Thickness	Monofilament Diameter	Bulk Box	Box A	Box B	Available Colors	Lbs/ 100'
1/8"	F6F0.13TB	.024"	.008"	10,000'	400′	100′	TB	0.20
1/4"	F6F0.25TB	.025"	.010"	3,000′	200′	100′	TB	0.60
3/8"	F6F0.38TB	.025"	.010"	1,200'	150′	75′	TB	1.20
1/2"	F6F0.50TB	.025"	.010"	800′	150′	75′	TB	1.40
3/4"	F6F0.75TB	.025"	.010"	500′	100′	50′	TB	1.60
1"	F6F1.00TB	.038"	.015"	400'	100′	50′	TB	2.00
1 1/4"	F6F1.25TB	.038"	.015"	250′	75′	25′	TB	2.40
1 1/2"	F6F1.50TB	.038"	.015"	200′	75′	25′	TB	2.70
2"	F6F2.00TB	.038"	.015"	150′	50′	25′	TB	3.60

Put-Ups

Flexible, Semi-Rigid Split Sleeving **Will Not Support Combustion**

Flame spread is a vital safety consideration in applications as diverse as home built aircraft wiring and safely managing sound & lighting cables at clubs, concerts and theaters. To accommodate these issues, and to provide unequaled flexibility and access, we've developed this unique sleeving product.


Self-extinguishing F6F fully complies with UL standard VW-1. The addition of a flame inhibitor to our triaxially braided F6 split sleeving provides the perfect solution to a wide range of cable management needs.

Easy slip over installation, complete access along the entire run, economy, durability and UL certified flame retardant make F6F ideal when the goal is to manage wires and cables safely and effectively.

The large overlap allows easy installation over splices and incline connectors without exposing wires and cables.



Colors Available: Black with White Tracer (TB)





www.techflex.com 800.323.5140 • 973.300.9242 • fax: 973.300.9409 104 Demarest Road • Sparta, NJ 07871







FLEXO® F6 FR



www.techflex.com



Abrasion Resistance High

Abrasion Test Machine Taber 5150

Abrasion Test Wheel Calibrase H-18

Abrasion Test Load 500g

Room Temperature 70°F

Humidity 63%

Slight Scuffing Visible **500 Test Cycles**

Visible Wear And Five **Broken Filaments** 1,200 Test Cycles

Material Destroyed 1,600 Test Cycles

Pre-Test Weight 3,469.8 mg

Post-Test Weight 3,114.0 mg


Test End Loss Of Mass Point Of Destruction 355.8 mg



Chemical Resistance

1=No Effect 4=More Affected 2=Little Effect 5=Severely Affected 3=Affected

3-Alleuleu	
Aromatic Solvents	2
Aliphatic Solvents	1
Chlorinated Solvents	3
Weak Bases	1
Salts	1
Strong Bases	2
Salt Water <i>0-S-</i> 1926	1
Hydraulic Fluid MIL-H-5606	1
Lube Oil MIL-L-7808	1
De-Icing Fluid MIL-A-8243	1
Strong Acids	3
Strong Oxidants	2
Esters/Keytones	1
UV Light	1
Petroleum	1
Fungus ASTM G-21	1
Halogen Free	Yes
RoHS	Yes
SVHC	None



Monofilament Diameter_ ASTM D-204	008015
Flammability RatingFMVSS-302 Approved	VW-1
Recommended Cutting_	Scissor/HK
Colors	1
Wall Thickness	.024038
Tensile Strength (Yarn)_ ASTM D-2256 Lbs	4-6.5
Specific Gravity ASTM D-	7921.38
Moisture Absorption % ASTM D-570	12
Hard Vacuum Data ASTM	E-595 at 10-5 torr
TML	.19
CVCM	.04
WVR	.06
Smoke D-Max ASTM E-662	275
Outgassing	Med
Oxygen Index	31

ÁŠTM D-2863

© 2014 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden.
Techflex product names and logos are registered trademarks of Techflex, Inc., unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable.
Techflex makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's only obligations are those in standard terms of sale for these products and Techflex will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions.

Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.

06-14