

7444



Specifications

- SAE-AMS-I-7444-A
- MIL-I-7444-D: Type I (clear only), • Type III, Class I & II
 - EU Directive 2000/53/EC (ELV)
- EU Directive 2011/65/EU (RoHS2)

PROPERTY **TYPICAL VALUE TEST METHOD** Durometer Hardness, Shore A (15 Seconds) 71 **ASTM D2240** Tensile Strength (psi) ASTM D412 2.100 Elongation (%) 400 ASTM D412 ASTM D297 **Specific Gravity** 1.18 Brittleness Temperature, Pass °C -68 ASTM D746 Flame Resistance (Average Burn Time, Sec.) 4 SAE-AMS-I-7444-A ASTM D149 Dielectric Strength (Volts/Mil) 500 Heat Aging (as a percent of un-aged specimen) Tensile Strength (%) 100 SAE-AMS-I-7444-A Elongation (%) 95

Note: MIL-I-7444-D was replaced by SAE-AMS-I-7444

Very Low Temperature PVC Tubing

Product Description

Gravline 7444 is a flexible polyvinyl chloride tubing designed to remain flexible in very low temperature environments.

This tubing finds uses typically in aircraft and aeronautical devices, but because it is a high quality tubing, it is suitable for any commercial applications which encounter very low temperatures.

Standard Packaging: Reels or Cut to Customer Specifications. Standard Color: Clear, Black, White Custom Sizes & Colors Available Upon Request

Features

- Operating Temperature is -68°C to 60°C
- Extreme Low Temperature Flexibility
- **Highly Flame Retardant**
- **Fungus Resistant**
- Lead-Free

The values listed in this bulletin, to the best of our knowledge, are accurate. They are typical performance results and are not intended to be used as design data. We disclaim all liability in connection with the use of information contained herein or otherwise.