

942 FLEX-GUARD PE/F

SERIES *Fray Resistant Expandable Monofilament Sleeving*



DESCRIPTION

- Braided sleeving produced from polyester PET (Polyethylene Terephthalate) monofilament
- Custom braided to resist fraying when scissor cut
- Tough yet lightweight protective sleeving
- UL recognized for use up to 125°C
- CSA approved and rated for use up to 125°C
- Standard color: Black

FEATURES

- Demonstrates excellent chemical and fungus resistance
- Provides good mechanical properties with additional coverage
- Resistance to abrasion and cut-through make it ideal for many industrial and electrical applications
- Excellent chemical resistance permits use in harsh fluid environments
- Open weave construction allows expansion above or below original diameter
- Easy to apply and slip on quickly over irregular shapes
- Good flexibility retained at low temperatures, allows for easy flexing in any direction
- Can neatly capture a number of different sized items within one length

APPLICATIONS

- Most commonly used over wires, wire bundles and harnesses, cable assemblies, flat ribbon cable, tubing and hoses to provide a tough, durable protection
- Open weave construction allows for complete drainage, prevents condensation and provides for dissipation of heat and moisture
- Ideal for application in machine tools, automatic equipment and robotics where wires and tubes are required to flex freely during operating cycles
- Suitable for exposure to all weather conditions

DIMENSIONS	PART NUMBERS (COLOR: BLACK)	SIZE NOMINAL ID	SIZE RANGE	APPROX. WEIGHT/1000 FT.	STD. SPOOL PUT-UP
	94220125	1/8"	1/8" - 1/4"	4.3 lbs.	500 ft.
	94220250	1/4"	3/16" - 3/8"	5.1 lbs.	500 ft.
	94220375	3/8"	1/4" - 1/2"	7.5 lbs.	250 ft.
	94220500	1/2"	3/8" - 3/4"	7.9 lbs.	250 ft.
	94220750	3/4"	5/8" - 1"	10.3 lbs.	250 ft.
	94221250	1-1/4"	1" - 1-1/2"	16.3 lbs.	250 ft.
	94221500	1-1/2"	1-1/4" - 2"	20.2 lbs.	250 ft.

The information provided above represents average values and is believed to be reliable. Alta Technologies, Inc. makes no warranties as to its accuracy and disclaims any liability in connection with its use. It is provided for general use only and should not be incorporated into any specific specifications.

FLUID RESISTANCE

Testing verifies that there is virtually no effect on the tensile strength and only a slight reduction in elongation (approx. 5%) of FLEX-GUARD PE/F when exposed to the following fluids: Cleaning Fluid, De-icing Fluid, Fuel Oil, Gasoline, Hydraulic Fluid, Lubricating Oil, Salt Water and Solvents.

TESTING

PROPERTIES

Tensile Strength
 Elongation
 Specific Gravity
 Moisture Absorption (24 hours)
 Shrinkage @ 180°C
 Max. Operating Temperature
 Melt Temperature
 Low Temperature Flexibility
 Flexural Modulus 10³ psi @ 73°F
 Fungus Resistance
 Copper Corrosivity

TEST METHOD

ASTM D-876
 ASTM D-876
 ASTM D-876
 ASTM D-570
 UL 224
 ASTM D-2117
 MIL I 23053-E
 ASTM D-790
 MIL STD 810 (508)
 MIL I 23053

PERFORMANCE

100,000 psi
 20%
 1.31
 0.08%
 4%
 125°C
 250°C
 -70°C
 400
 No Growth
 No Effect



ALTA TECHNOLOGIES, INC.

P.O. Box 100, Pennington, NJ 08534 | www.altatechinc.com | E: info@altatechinc.com | P: 609-538-9500 | F: 609-538-9501