

976 ALTA-FLEX™ TUFF

SERIES Heavy Duty Expandable Nylon Monofilament Sleeving

DESCRIPTION

- Custom braided sleeving produced with a uniquely shaped polyamide monofilament
- Extra durable protection for excessive abrasion applications
- UL recognized
- Operating temperature 150°C (302°F)
- Standard color: Black

FEATURES

- Exceptional abrasion resistance
- Excellent flexibility
- Demonstrates good chemical resistance
- Excellent chemical resistance permits its use in harsh fluid environments
- Expandable for ease of installation over irregular shapes and enlarged end fittings
- Uniquely shaped monofilament provides smooth, slick surface resisting snags when dragged over rough surfaces



APPLICATIONS


- Most commonly used over industrial hoses, harnesses, and cable assemblies to provide durable protection in excessive abrasion applications
- Open weave construction allows for complete drainage, prevents condensation and provides for dissipation of heat and moisture
- Suitable for exposure to all weather conditions

DIMENSIONS	PART NUMBERS (COLOR: BLACK)	SIZE NOMINAL ID	SIZE RANGE	APPROX. WEIGHT/1000 FT.	STD. SPOOL PUT-UP
	97620500	1/2"	3/8" - 5/8"	13.6 lbs.	250 ft.
	97620750	3/4"	5/8" - 1"	20.5 lbs.	250 ft.
	97621000	1"	7/8" - 1-1/4"	22.0 lbs.	250 ft.
	97621250	1-1/4"	1" - 1-1/2"	25.0 lbs.	100 ft.
	97621500	1-1/2"	1-1/4" - 1-3/4"	32.0 lbs.	100 ft.
	97621750	1-3/4"	1-1/2" - 2"	39.7 lbs.	100 ft.
	97622000	2"	1-3/4" - 2-3/4"	44.0 lbs.	100 ft.

The information provided above represents average values and is believed to be reliable. Alta Technologies, Inc. makes no warranties as to its accuracy and disclaims any liability in connection with its use. It is provided for general use only and should not be incorporated into any specific specifications.

FLUID RESISTANCE

ALTA FLEX™ TUFF offers good chemical resistance to hydrocarbons, common automotive oils and fuels, aromatic solvents, aliphatic solvents and refrigerants



TESTING

PROPERTIES

Tensile Strength
 Elongation
 Specific Gravity
 Moisture Absorption (24 hours)
 24 hour/Shrinkage @ 350°F
 Melt Temperature

TEST METHOD

ASTM D-876
 ASTM D-638
 ASTM D-792
 ASTM D-570
 ASTM D-2117

PERFORMANCE

55,000 psi
 25%
 1.12
 1.1%
 5%
 265°C



ALTA TECHNOLOGIES, INC.

P.O. Box 100, Pennington, NJ 08534 | www.altatechinc.com | E: info@altatechinc.com | P: 609-538-9500 | F: 609-538-9501