



AUTOMOTIVE

Inventing *the Future* of Wire and Cable

EXRAD 180B

Powertrain Cable
-40 - 180°C

EXRAD 180B is a high performance fluid blocking wire built to handle the high temperature fluid environments in engines and transmissions. It is an irradiation cross-linked fluoropolymer with impressive properties. EXRAD 180 is extremely fluid resistant even at temperatures up to 150°C. It significantly reduces wire and routing headaches because it is more heat resistant and tough than TXL. It is an excellent, cost effective replacement for TFE, FEP or Tefzel insulated wire. EXRAD is rated at 180° C, but it survives temperatures to 270° C and higher for short periods of time. It is safer in overload conditions, because it will not melt. EXRAD 180B has silicone blocked conductor to prevent moisture and other fluids to wick through the wiring system.

Given today's longer warranties, you need a wire that will last longer than ever before. New standards are now requiring 10,000 hour heat age test. EXRAD has a life expectancy over 12,000 hours at 160° C. For commercial vehicle and heavy duty equipment EXRAD has an expected life of 24,000 hours at 150° C

EXRAD process very well on automated high speed cut and strip equipment. The end result is an automotive wire ideally suited in applications where heat protection, high temperature fluid resistance, fluid blocking, long life and less expensive wiring harness are required.

Benefits and Features

- Excellent anti-capillary properties
- Excellent Cut-Through Resistance
- High Temperature Fluid Resistance
- Passes 1000 hours @150° C in Transmission Fluid
- 40° C to 180° C Temperature Range
- Superior Processing
- RoHS Compliant

Applications

- Including but not limited to:
- Automatic Transmissions
- Diesel Fuel Injectors
- Sensors
- Locations inside Diesel and Gasoline engines

Part Number	Standard Conductors Bare Copper	Nom. Dia		Insulation Thickness		Nom. OD		Finished Weight (lbs/mft)	Ampacity
		in.	mm.	in.	mm.	in.	mm.		
EXRAD-XBT-24XX	24 (7/32)	.024	.61	.016	.41	.054	1.37	2.91	6
EXRAD-XBT-22XX	22 (7/30)	.031	.79	.016	.41	.063	1.60	3.96	11
EXRAD-XBT-20XX	20 (7/28)	.038	.97	.016	.41	.070	1.78	5.58	15
EXRAD-XBT-18XX	18 (19/30)	.049	1.19	.016	.41	.081	1.98	7.34	21
EXRAD-XBT-16XX	16 (19/29)	.057	1.45	.016	.41	.089	2.26	10.25	28
EXRAD-XBT-14XX	14 (19/27)	.071	1.81	.016	.41	.103	2.62	15.16	46
EXRAD-XBT-12XX	12 (19/32)	.095	2.41	.018	.46	.128	3.25	25.06	60
EXRAD-XBT-10XX	10 (19/30)	.112	2.84	.018	.46	.156	3.96	38.65	80

*Ampacity 150°C rated single-insulated conductor in free air at 40°C ambient air temperature.

www.champcable.com



Champlain Cable Corporation
175 Hercules Drive
Colchester, Vermont 05446

P 800.451.5162
F 802.654.4224
sales@champcable.com



AUTOMOTIVE

Inventing *the Future* of Wire and Cable

EXRAD 180 Powertrain

Property / Attribute		SAE J-1128 TXL Req.	EXRAD 180 18 AWG Typical Performance
Flex Life			
Flex Test	Per Modified ISO 14572	NA	NA
Dielectric Strength			
Dielectric Test	Wet Dielectric after 5 hour soak	1 kV 1 min.	5 kV 30 min.
Flame Resistance			
Flame Test	Burn time after removal of gas burner	70 sec max.	1 sec
Thermal Performance			
Cold Bend	4 hours at temperature no cracks / breakdown	-40°C	-40°C
Temperature Rating	240 Hours @213°C heat aging	155°C	213°C
Temperature Rating	3000 Hours @180°C	125°C	180°C
Mechanical Properties			
Tensile	psi	1500 min.	3800
Elongation	%	150 min.	320
Abrasion	Sand Paper Resistance Length in.	10 min.	31
Abrasion	Scrape Cycles	None	1400
Pinch	Pounds	5.5 min.	26
Hydrolysis Resistance			
Hydrolysis Resistance	168 Hours @ 75°C saltwater immersion and 48 volts dc, no cracks, no dielectric failure	pass	pass
Ozone Resistance			
Ozone Test	192 Hours @ 65°C 100 pphm no cracks	Pass	Pass
Fluids			
Engine Oil	ASTM D471, IRM-902	115 +/-3 °C	15% Max.
Gasoline	ASTM D471 Ref. Fuel C	23 +/-5 °C	15% Max.
Brake Fluid	SAE-J-1703	50 +/-5 °C	None
Ethanol	85% Ethanol +15% ASTM D471, Ref. Fuel C	23 +/-5 °C	15% Max.
Diesel Fuel	ASTM D471, 90% IRM-903 + 10% p-xylene	23 +/-5 °C	15% Max.
Power Steering	ASTM D471, IRM-903	50 +/-3 °C	30% Max.
Auto Transmission	Citgo #33123 SAE-J311	50 +/-3 °C	25% Max.
Methanol		23 +/-5 °C	25% Max.
Engine Coolant	50% Ethylene Glycol + 50% distilled Water	50 +/-3 °C	15% Max.
Battery Acid	H ₂ SO ₄ Specific Gravity = 1.260 +/- .005	23 +/-5 °C	5% Max.

We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability your products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purpose. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss and damage arising from the handling and use of our products whether used alone or in combination with other products.

www.champcable.com



Champlain Cable Corporation
175 Hercules Drive
Colchester, Vermont 05446

P 800.451.5162
F 802.654.4224
sales@champcable.com