



A Medium Density Polyethylene Compound

TYPICAL APPLICATIONS:

Wire Troughs, and other automotive components.

Product Description:

Properties shown below for this filled blend are typical for a medium density polyethylene compound. This product is designed for blow molding and extrusion processes.

Delfingen Product Reference: PE10

Colors available: Natural (M0012), Black (M0013)
Gray, Red, White, Yellow.

Features and Options:

- High Impact
- Good Flexibility
- Chemical Resistance
- 85°C continuous rating (3000 hours)
- short term : 115°C - 168 hours

Physical Properties	Test Methods	Values	Unit
Melt Flow Index (190°C, 21.6 kg)	ASTM D1238	>0.9	g/10 min
Specific Gravity	ASTM D792	0.94	g/cm ³
Tensile Strength, Yield (50 mm/min)	ASTM D638	15	MPa
Tensile Elongation, Break (50 mm/min)	ASTM D638	>450	%
Flexural Modulus, secant (1.3 mm/min)	ASTM D790	350	MPa
Flammability (3mm)	UL94	HB	-
	FMVSS 302	<102	mm/min

This raw material is designed to meet:

- Ford ES-XU5T-14A099-AA RevB - 85°C-
- UTMS 18013
- Yazaki YPES 16-122 - 85°C-
- ESB-M4D152-A and ESB-M4D153-A
- DELPHI M2092 / M3421 / C0836

IMDS report available on demand.

*This material must be compliant with **ELV directive 2000/53/EC and its Annexes**. A maximum concentration value up to 0.1% by weight and per homogeneous material for lead, hexavalent chromium and mercury and up to 0.01% by weight per homogeneous material for cadmium shall be tolerated provided these substances are not intentionally introduced. No intentionally introduced amount is tolerated.*

The data listed here falls within normal range of properties, but they should not be used for setting specific limits or used as a basis for design. The applications and conditions for use of this product including technical assistance and information are beyond our control. Users of this product are responsible for evaluating this product to ensure their own satisfaction that it is suitable for their intended uses. All information is given without warranty or guarantee. Before working with this product, users must read and familiarize themselves with the available health, safety and environmental information that is available regarding product hazards, proper use and handling.