

Drossbach Technical Data Sheet For Flexible Convuluted Tubing / Conduit



Data Sheet	TD-013 "PE or DE" Polyethylene		
Revision:	4	Date:	06/13/16
Base Material:	Polyethylene		
Material Code:	PE or DE		

Our commitment to quality is our commitment to success

Product Description

Flexible convuluted tubing / conduit manufactured from a blend of low density polyethylene and linear low density polyethylene resins.

Performance Enhancers

Flame Retardant	No
UV Inhibitor	No
Heat Stabilizer	No

Performance Characteristics

Flexibility	Excellent
Abrasion Resistance	Good
Chemical Resistance	Good See Chemical Resistance Report: CR-013
Continuous Operating Temperature	-40 to +85C (-40 to +185F) Min. 3000 Hrs.
Short Term" Operating temperatures	-40 to +93C (-40 to +200F) Max. 168 Hrs

Typical Physical Properties

Test Method	Value	Units
Specific Gravity/Density	ASTM D792	0.924
Elongation @ Break	-	-
Elongation @ Yield	-	-
Tensile Strength @ 25C	-	-
2% Secant Modulus	-	-
Flexural Modulus	-	-
Melting Point	-	-
Notched Izod Impact Test	-	-
Heat Deflection Temperature @66psi	-	-
Heat Deflection Temperature @264psi	-	-

Material Certifications

Delphi / Packard	-
Ford	-
General Motors	-
Chrysler	-
ASTM	-
Underwriters Laboratory	-
FMVSS 302	-
Other	-

Notes

- (1) Drossbach does not claim or state any UV life or warranty unless stated above in the "Other" section", as we do not have any control over its end use environment.
- (2) All "UL" and FMVSS 302 flame ratings are for the resin used to manufacture our product, not for our end product. The ratings are created by testing standard "UL" and "FMVSS" plaque specimens, not tubing samples.
- (3) Compliant with the European Union's Directive 2002/95/EU (RoHS), REACH Directive and the Conflict Minerals Initiative.
- (4) Only product designated as UL 94 "V0" in the Material Certification section above can be certified as non-Halogenated product.
- (5) If a product is designated as flame retardant but has no material certification listed, this product is a Drossbach internally blended material blended with a flame retardant additive. It is tested to an internal flame test (DR-006) that holds no claimed warranty.

Drossbach N.A. Inc.
 PO Box 2000
 157 N. Murray St.
 Trenton, Ontario Canada
 K8V 6G7
 Phone: (613) 394-4817 Fax: (613) 394-5516

Web Site Address: <http://www.drossbach.com>
Email: info@drossbachllc.com
An IATF 16949 and ISO-9001 Registered Company

Drossbach LLC
 1500 Commerce Drive
 Stow, OH, 44224 USA
 Phone: (330) 688-8460
 Toll Free: (800) 841-5804
 Fax: (330) 688-8465

This data is supplied for general product information / knowledge only. Drossbach N.A. does not state any warranty regarding the accuracy of this information. This document only represents a summarization of technical data supplied by the manufacturers of the base materials we use to make our finished product. The data listed in this document should not be used as a basis for a customer's product design limitations. Users of this product are also responsible for the full evaluation of this product to make sure it is adequate for all their design requirements. Prior to using this product, the user should familiarizing themselves with the available Health, Safety and Environmental information. This document and the information contained herein is proprietary to Drossbach N.A. Inc. It shall not be reproduced, copied or disclosed in whole or part, nor can it be used for manufacturing or any other purpose without the written permission of Drossbach N.A. Inc.