
APPLICATION

These lightweight, high temperature airframe and avionics wires utilize an insulation of cross-linked, modified ethylene tetrafluoroethylene copolymer (ETFE). The insulation resists high PH cleaning fluids, fuels, lubricating oils, and many other chemicals. These wires can withstand temperature test extremes ranging from cold bend at -65°C through aging at 300°C for 7 hours. These wires are a mechanically tough, flame retardant, and weight saving solution to many aerospace applications.

SAE AS22759/45 & 46 Cross-Linked ETFE - 600V, 200°C

Lightweight Wall



Conductor Nickel plated copper or high strength allo (various strandings)

CONDUCTOR

Nickel plated copper for /45 and nickel plated high strength copper alloy for /46, stranded as listed above.

INSULATION

Single layer of irradiation crossnked extruded ETFE meeting he requirements of the above pecification.

		ľ
1	1	

	Conductor			Conductor		Nom.				
Part Number	Size		Strand-	Resistance @20°C		Diameter		Weight		
	AWG	mm ²	ing		Ω/kft	Ω/km	Inch	mm	lbs/kft	kg/km
22759/45-26-X	26	.15	19/38	NC	42.2	138	.032	.81	1.4	2.08
22759/45-24-X	24	.24	19/36		25.9	85.0	.037	.94	2.0	2.98
22759/45-22-X	22	.38	19/34		16.0	52.5	.043	1.09	2.8	4.17
22759/45-20-X	20	.62	19/32		9.77	32.1	.050	1.27	4.3	6.40
22759/45-18-X	18	.96	19/30		6.10	20.0	.060	1.52	6.5	9.67
22759/45-16-X	16	1.23	19/29		4.76	15.6	.068	1.73	8.3	12.3
22759/45-14-X	14	1.94	19/27		3.00	9.84	.085	2.16	13.0	19.0
22759/45-12-X	12	3.08	37/28		1.98	6.50	.103	2.62	19.7	29.0
22759/46-26-X	26	.15	19/38	NA	49.4	162	.032	.81	1.4	2.08
22759/46-24-X	24	.24	19/36		30.1	98.8	.037	.94	2.0	2.98
22759/46-22-X	22	.38	19/34		18.6	61.0	.043	1.09	2.9	4.31
22759/46-20-X	20	.62	19/32		11.4	37.4	.050	1.27	4.4	6.55

X = color. See page 67 for color designator.

The above part numbers represent the more popular constructions. However, other designs are available upon request. All products are manufactured to meet RoHS compliance. For exceptions, please contact our sales department.

APPROVALS AND RATINGS

200°C conductor temperature, 600 volt. SAE AS22759/45 and /46.

CABLES

Cables may be assembled using the requirements of NEMA WC 27500, using Type SS and ST components of /45 and /46 respectively.

