

# 1151-FR Grade A

- Class 200°C
- Available Grades; A & 15KV
- UL Recognized Component for 200°C, 600 Volts and VW-1 compliant under UL File No. E63446 (Grade A).
- CSA File #058703
- NEMA 5

- Applicable Documents ASTM D-350 ASTM D-372 NEMA TF-1 MIL-I-3190/6
- Available in Red, Black, Natural and White - Specialty Colors Available Upon Request.
- Available in AWG sizes #24 through 2" I.D.

## Silicone Rubber Coated Fiberglass Sleeving

Ben-Har<sup>™</sup> 1151-FR sleeving is an extremely flexible sillicone rubber coated fiberglass sleeving with outstanding flame retardant properties. 1151-FR A Grade is a UL Recognized Component, meeting VW-1 flammability requirements, recommended for Class H (200°C) systems. The special combination of a smooth fiberglass bore and flexible, elastomeric silicone coating allows this sleeving to expand and conform over larger dimensions, assuring a snug fit, permanent placement, and elastic self-fitting on components or terminals. The excellent bond of rubber coating to the braid insures against damage from rough assembly handling.

Ben-Har<sup>™</sup> 1151-FR is resistant to acids, alkalis, organic solvents, and aliphatic hydrocarbons. Slight swelling is produced by aromatic solvents and clorinated hydrocarbons. Ketones and esters may cause deterioration. Ben-Har<sup>™</sup> 1151-FR is compatible with common Class H insulating varnishes.

Ben-Har<sup>™</sup> 1151-FR is commonly used in appliance assemblies, wire harnesses, transformer leads, power supplies, and motor coil and heater leads. This product is also available in Heavy wall constructions (15KV) for high voltage use and can be obtained in colors for identification and appearance.

### **Certified to ISO 9001 Standards**

www.atkinsandpearce.com

Product also known as: Ben-Har<sup>™</sup> 1151-FR Grade A

## Performance Data – Ben-Har<sup>™</sup> 1151-FR Grade A

#### **Product Specifications**

NEMA Size	Nominal Diameter	Nominal Diameter	Bentley- Harris	Maximum Diameter	Minimum Diameter
	(inches)	(mm)	Part Number	(inches)	(inches)
24	0.022	0.56	32001924XX	0.027	0.020
22	0.027	0.69	32001922XX	0.032	0.025
20	0.034	0.86	32001920XX	0.039	0.032
18	0.042	1.07	32001918XX	0.049	0.040
16	0.053	1.35	32001916XX	0.061	0.051
14	0.066	1.67	32001914XX	0.074	0.064
12	0.085	2.59	32001912XX	0.091	0.081
10	0.106	2.69	32001910XX	0.112	0.102
9	0.118	2.10	32001909XX	0.124	0.114
8	0.133	3.38	32001908XX	0.141	0.129
7	0.148	3.76	32001907XX	0.158	0.144
6	0.166	4.22	32001906XX	0.178	0.162
5	0.186	4.72	32001905XX	0.198	0.182
4	0.208	5.28	32001904XX	0.224	0.204
3	0.234	5.94	32001903XX	0.249	0.229
2	0.263	6.68	32001902XX	0.278	0.258
1	0.294	7.47	32001901XX	0.311	0.289
0	0.330	8.38	32001900XX	0.347	0.325
3/8"	0.375	9.52	32001010XX	0.399	0.375
7/16"	0.438	11.12	32001011XX	0.462	0.438
1/2"	0.500	12.70	32001013XX	0.524	0.500
5/8"	0.625	15.87	32001016XX	0.655	.0625
3/4"	0.750	19.05	32001019XX	0.786	0.750
7/8"	0.875	22.22	32001022XX	0.911	0.875
1"	1.000	25.40	32001025XX	1.036	1.000
1 1/4"	1.250	31.75	32001032XX		
1 1/2"	1.500	38.10	32001038XX		
*2"	2.000	50.80	32001051XX		

XX = Color Code

\* Size not available in white

02 = White

03 = Black

14 = Red iron oxide

°C	°F
538	1000
527	980
516	960
504	940
493	920
482	900
471	880
460	860
449	840
438	820
427	800
416	780
404	760
393	740
382	720
371	700
360	680
349	660
338	640
327	620
316	600
304	580
293	560
282	540
271	520
260	500
249	480
238	460
227	440
216	420
204	400
193	380
182	360
171	340
160	320
149 138	300
138	280
127	260 240
104	220
99	210
88	190
77	170
66	150
54	130
43	110
38	100
35	95
30	86
25	77
20	68
15	59
10	50
5	41
0	32
-5	23
-10	14
-15	5
-18	0
-20	-4
-40	-40
	70
-60	-76

The information and illustrations given herein are believed to be reliable. Atkins and Pearce, Inc. makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Atkins and Pearce's only obligations are those set forth in the Standard Terms and Conditions of sale for this product and Atkins and Pearce will not be liable for any consequential or other damages arising out of the use or misuse of this product. Users should make their own evaluation to determine the suitability of the product for specific applications.