



SM3-13 Clear, 2:1 Shrink Ratio Flexible Polyolefin

Product Overview:

SumiMark® SM3-13 heat shrink tubing is a markable product, manufactured to the highest quality standards. SumiMark® SM3-13 tubing product meets all requirements of SAE AMS-DTL-23053/5, Class 2. This product also meets print adherence requirements of SAE-AS5942, when used in conjunction with SumiMark® Marking Systems and SumiMark® ribbons.

Specifications:

SAE AMS-DTL-23053/5, Class 2 compliant

Recommended Printer & Ribbon:

SumiMark® Marking System Models III or IV
Ribbon SumiMark® SM3

Print Performance:

Adherence: SAE-AS5942
MIL-STD-202G, Method 215J
Store in original packaging

Applications:

- Wire identification
- Wire protection
- Fluid resistance
- Strain relief
- Abrasion protection

Product Features:

- 2:1 Shrink Ratio
- Operating temperature range -55°C to $+135^{\circ}\text{C}$ and up to 200°C for short durations
- Continuous format for cut-to-length requirements and cost savings
- RoHS/RoHS2 compliant
- Non-flame retarded
- Colors—clear only



915 Armorlite Drive
San Marcos, CA 92069-1440

T: 800.758.3515
F: 800.758.3517
E: customerservice@seipusa.com
W: www.seipusa.com



SM3-13

Clear, 2:1 Shrink Ratio Flexible Polyolefin

Technical Specifications:

Property	Test Method	Requirement
Tensile strength (psi)	ASTM D 638	1500 min.
Elongation (%)	ASTM D 638	200 min.
Specific gravity	ASTM D 792	1.0 max.
Low temperature flex (-55° C)	AMS-DTL-23053	no cracking
Heat shock (250° C, 4 hrs.)	AMS-DTL-23053	no cracking
Heat resistance (175° C, 168 hrs.)		
Elongation (%)	ASTM D 638	100 min.
Secant modulus (psi)	ASTM D 882	2.5 X 10 ⁴ max.
Longitudinal change (%)	AMS-DTL-23053	+/- 5
Electrical:		
Dielectric strength (volts/mil)	ASTM D 876	500 min.
Volume resistivity (ohm-cm)	ASTM D 876	1.0 X 10 ¹⁴ min.
Chemical:		
Corrosion (175° C, 16 hrs.)	AMS-DTL-23053	no corrosion
Water absorption (%)	ASTM D 570	0.5 max.
Fluid resistance (23° C, 24 hrs.)		
Tensile strength (psi)	AMS-DTL-23053	1000 min.
Shrink temperature, nominal		115° C
Specification references:		
AMS-DTL-23053/5, Class 2		
SAE AS5942		

Standard Sizes:

Size	ID Min (As Supplied)		ID Max (After Recovery)		Wall Thickness Nom (After Recovery)	
	Inch	MM	Inch	MM	Inch	MM
1/16	.063	1.6	.031	0.8	.017	0.43
3/32	0.09	2.4	.046	1.2	.020	0.51
1/8	.125	3.2	.062	1.6	.020	0.51
3/16	.187	4.8	.093	2.4	.020	0.51
1/4	.250	6.4	.125	3.2	.025	0.64
3/8	.375	9.5	.187	4.8	.025	0.64
1/2	.500	12.7	.250	6.4	.025	0.64
3/4	.750	19.1	.375	9.5	.030	0.76
1	1.00	25.4	.500	12.7	.035	0.89
1 1/2	1.50	38.1	.750	19.1	.040	1.02
2	2.00	50.8	1.00	25.4	.045	1.14

Standard Colors: Clear only

Standard Package: Spooled

How to Order: Type of Material

Example:

SM3-13

Size

1/4

Color

Clear

Packaging

S