CPX 201



INSULATE SEAL PROTECT 3:1 Shrink Ratio







THIN WALL CROSS-LINKED POLYOLEFIN

Yellow and green striped heat shrink tubing that is flexible and flame retardant

FEATURES AND BENEFITS

- High shrink ratio: 3:1
- Striped color combination designates international electrical grounding
- Flame retardant
- Resistant to common fluids and solvents
- Flexible
- Continuous operating temperature: -55°C to 135°C
- Shrink temperature: 90°C

STANDARDS

- UL 224, 125°C
- CSA C22.2 No. 198.1, 125°C
- SAE-AMS-DTL-23053/5 Class 1 (material only)
- AMS 3636


TYPICAL APPLICATIONS

- Identify ground wire and terminals
- Electrical insulation of in-line connections



DIMENSIONS

	EXPANDED INTERNAL DIAMETER (MIN.) D		RECOVERED					
ORDER NUMBER			INTERNAL DIAMETER (MAX.) d		WALL THICKNESS (NOM.) W		LENGTHS	
	MM	IN	ММ	IN	MM	IN	М	FT
0125	3.2	1/8	1.0	0.039	0.55	0.022	150	500
0187	4.8	3/16	1.5	0.059	0.60	0.024	60	200
0250	6.4	1/4	2.0	0.079	0.65	0.026	150	500
0375	9.5	3/8	3.0	0.118	0.75	0.030	60	200
0500	12.7	1/2	4.0	0.157	0.75	0.030	60	200
0750	19.0	3/4	6.0	0.236	0.85	0.033	30	100
1000	25.4	1	8.0	0.315	1.00	0.039	30	100
1535	39.0	1.50	13.0	0.512	1.15	0.045	30	100



ORDERING

- Select a dimension which will shrink snugly over the component to be covered. If recovery is restricted the resultant wall thickness will be less than specified.
- Select options:
 - Colour: Yellow/green stripesPrinting: Printed or Unprinted
 - Length: Continuous reels
- Please specify the product name, order reference number and options you require
- Order Example: CPX 201, 0250, yellow/green stripes, unprinted, 500 ft lengths

Please contact your Customer Service Representative for information on custom colours, sizes, lengths and material data sheet.

believed to be reliable. We advise, and conditions of solid feparates in respect of the accordance is reliable. We advise, and conditions of solid feparates in respect of the accordance is reliable to the reliable in the reliable of the reliable to the reliable in the reliable is reliable to the reliable in the reliable is reliable in the reliable in the reliable is reliable in the reliable in the reliable in the reliable in the reliable in any indicators of the reliable in the reliable in

USA: 800.422.6872 Canada: 800.845.6808 www.dsgcanusa.com