

Silicone - Type 3304 (AWM)

High Temperature / High Voltage Lead Wire

UL: 200°C, 10KV

CSA: 200°C, 10KV, AWM I A/B



IEWC Part Number	AWG	Stranding	Nominal Insulation Thickness		Nominal O.D.		Approx. Weight	
			in	mm	in	mm	lbs/1k ft	kg/km
3304/22	22	7/30	0.040	1.0	0.125	3.2	9	13
3304/20	20	7/28	0.040	1.0	0.133	3.4	14	21
3304/18	18	7/26	0.040	1.0	0.143	3.6	13	19
3304/16	16	7/.0192	0.040	1.0	0.153	3.9	17	25
3304/14	14	7/.0242	0.040	1.0	0.167	4.2	23	34
3304/12	12	19/.0185	0.040	1.0	0.184	4.7	32	48

Notes

- Soft-annealed, tinned copper conductor
- Silicone rubber insulation
- A variety of insulation colors available

Alternative Constructions

- Soft-annealed, silver-plated copper conductor

Applications

For use in electronic and appliance applications. Rated for continuous use up to 200°C.